

Pertamina Asphalt Product Specification

Asphalt Pen 60/70				
NO	Spesification	Method	Min	Max
1	Specific Gravity at 60/60°F	ASTM D - 70	1	-
2	Ductility at 25 °C cm	ASTM D - 113	100	-
3	Flash Point C.O.C °C	ASTM D - 92	200	-
4	Loss on Heating at. 5 Hours/163°C % wt	ASTM D - 6	-	0,4
5	mm	ASTM D - 5	60	70
6	Penetration after Loss on Heating %	ASTM D - 5	75	-
7	Solubility in CCL % wt	ASTM D - 2042	99	-
8	Softening Point Ring and Ball °C	ASTM D - 36	48	58