

Slack Wax Specification

NO	SPECIFICATION		METHOD	SPO	LMO	MMO	DAO
1	SPECIFIC GRAVITY 70°C		ASTM D - 1298	0.77 - 0.83	0.795 - 0.85	0.785 - 0.845	0.825 - 0.875
2	VISCO KINEMATIC AT 100°C	CST	ASTM D - 445	3.100 - 4.200	4.700 - 5.700	8.3 - 9.4	18.5 - 22.5
3	FLASH POINT PMCC	°C	ASTM D - 93	MIN. 145	MIN. 200	MIN. 220	MIN. 240
4	OIL CONTENT	%WT	ASTM D - 721	MAX. 28.00	MAX. 35	MAX. 40	MAX. 20.00
5	MELTING POINT, °C	°C	ASTM D - 87	47.0 - 53.0	53.0 - 58.0	58 - 64	69.0 - 74.0
6	CONGEALING POINT, °C	°C	ASTM D - 938	46.0 - 53.0	53.0 - 58.0	58 - 64	69.0 - 74.0
7	SULFUR CONTENT, % WT	%WT	ASTM D - 1552	MAX. 0.30	MAX. 0.20	MAX. 0.20	MAX. 0.20
8	COLOR ASTM		ASTM D - 1500	MAX. L 1.0	MAX. 1.5	MAX. 4.5	MAX 5