

Polypropylene Pertamina Spesification

Grade Production	Melt Flow Rate Avg		Tensile Yield Strenght	Flexural Modulus	Hardness (Rockwell)	Softening Point (Vicat)	Deflection Temp. at 66 psi
METHODUNITS	ASTM D1238 gr / 10 min.	ASTM D1505 gr / ml	ASTM D638 kg / cm ²	ASTM D790 kg / cm ³	ASTM D785 R Scale	ASTM D1525 °C	ASTM D648 °C
POLYTAM FILM GRADEPF - 1000	10	0,91	380	16000	100	155	110
POLYTAM YARD GRADEPY - 240	2,4	0,91	380	15000	95	155	110
POLYTAM INJECTION GRADEPI	11	0,93	380	16000	100	155	110